

claim 6

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
4 July 2002 (04.07.2002)

PCT

(10) International Publication Number
WO 02/051941 A1

(51) International Patent Classification⁷: C09B 1/58, C08K 5/00

(21) International Application Number: PCT/EP01/14692

(22) International Filing Date:
13 December 2001 (13.12.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
2508/00 22 December 2000 (22.12.2000) CH
247/01 13 February 2001 (13.02.2001) CH

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(71) Applicant (*for all designated States except US*): CIBA SPECIALTY CHEMICALS HOLDING INC. [CH/CH]; Klybeckstrasse 141, CH-4057 Balse (CH).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): SUTTER, Peter [CH/CH]; Seemättlistrasse 14/2, CH-4132 Muttens (CH). AESCHLIMANN, Peter [CH/CH]; Sandweg 16, CH-4123 Allschwil (CH).


(74) Common Representative: CIBA SPECIALTY CHEMICALS HOLDING INC.; Patentabteilung, Klybeckstrasse 141, CH-4057 Basel (CH).

Published:


- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: ANTHRAQUINONE DYES, PREPARATION THEREOF AND USE THEREOF



(I)



(II)

(57) Abstract: The present invention relates to anthraquinone dyes of the formula (I) where R₁ is hydrogen, R₂ is hydrogen or CO-C₂C₆alkyl moiety may be substituted by carboxyl, or is (II) wherein R₆ is hydrogen, C₁-C₄alkyl, hydroxyl, carboxyl or halogen, R₇ is hydrogen, C₁-C₄alkyl or halogen and R₈ is hydrogen or C₂-C₃alkyl or when R₄ is halogen R₄ may be methyl or halogen, R₃ is hydrogen or halogen, R₄ is hydrogen or halogen and n is (0), (1) or (2), with the proviso that R₃, R₄, R₆, R₇ and R₈ are not all hydrogen at one and the same time, processes for their preparation and their use for dyeing or printing hydrophobic fibre materials or for preparing coloured plastics or polymeric colour particles.


ANTHRAQUINONE DYES, PREPARATION THEREOF AND USE THEREOF

The present invention relates to anthraquinone dyes, their preparation and their use for dyeing or printing manufactured natural polymer or synthetic hydrophobic fibre materials and for preparing coloured plastics or polymeric colour particles.

Anthraquinone dyes and their use for dyeing manufactured natural polymer or synthetic hydrophobic fibre materials are known. Also known is the use of anthraquinone dyes for mass colouring synthetic materials (plastics). However, it has been determined that these dyes do not always fully meet the highest requirements, especially with regard to hot light fastness, heat stability and/or colour strength. There is accordingly a need for novel dyes which produce hot light fast, heat stable and strong dyeings or prints and have good general fastnesses.

It has now been found that, surprisingly, the dyes of the invention substantially meet the criteria indicated above.

The present invention accordingly provides anthraquinone dyes of the formula



where

R₁ is hydrogen,

R₂ is hydrogen or -CO-C₂-C₆alkyl wherein the C₂-C₆alkyl moiety may be substituted

by carboxyl, or is wherein R₆ is hydrogen,

- 2 -

C₁-C₄alkyl, hydroxyl, carboxyl or halogen, R₇ is hydrogen, C₁-C₄alkyl or halogen and R₈ is hydrogen or

C₂-C₃alkyl or when R₄ is halogen R₈ may be methyl or halogen,


R₃ is hydrogen or halogen,

R₄ is hydrogen or halogen and


n is 0, 1 or 2,

with the proviso that R₃, R₄, R₆, R₇ and R₈ are not all hydrogen at one and the same time.


Preferred dyes of the formula (1) are dyes of the formulae



(2)




(3)




(4)


- 3 -




(5)




(6)




(7)




(8)




(9)



(10)




(11)




(12),

- 5 -




(13) and



(14).

The present invention further provides a process for preparing the anthraquinone dyes of the formula (1) according to the invention.

The anthraquinone dyes according to the invention are obtainable similarly to known compounds, for example by reacting a compound of the formula



(50)


where

R_1 , R_2 and R_4 are each as defined under the formula (1) and Hal is halogen, preferably chlorine, with a compound of the formula



where

R_3 and n are each as defined under the formula (1), or by reacting a compound of the formula



where

R_3 , R_4 and n are each as defined under the formula (1), with the compound of the formula



where


R_6 , R_7 and R_8 are each as defined under the formula (1), according to known processes.

The compounds of the formulae (50) to (53) are known or preparable according to generally known methods.

The present invention further provides a dye mixture comprising two or more structurally different anthraquinone dyes of the formula (1).

Preference is given to a dye mixture comprising two structurally different anthraquinone dyes of the formula (1).

Particular preference is given to a dye mixture comprising the anthraquinone dyes of the formulae (4) and (13) and the dye of the formula



(15).

The dye of the formula (15) is known and preparable according to generally known methods.

The amount of the individual dyes in the dye mixtures according to the invention can vary within wide limits, for example from 95:5 to 5:95 parts by weight, especially from 70:30 to 30:70 parts by weight and particularly from 55:45 to 45:55 parts by weight of the individual dyes in a dye mixture comprising two anthraquinone dyes of the formula (1) according to the invention.

Important dye mixtures comprise 30 to 40 per cent by weight of the anthraquinone dye of the formula (4), 30 to 40 per cent by weight of the anthraquinone dye of the formula (13) and 30 to 40 per cent by weight of the anthraquinone dye of the formula (15), based on 100 per cent by weight of the dye mixture.

Particularly important dye mixtures comprise the anthraquinone dyes of the formulae (4), (13) and (15) in a weight ratio of 1:1:1.

The dye mixtures comprising two or more structurally different anthraquinone dyes of the formula (1) may be prepared by, for example, simply mixing two or more of the above-described anthraquinone dyes, for example anthraquinone dyes of the formulae (4) and (13) or (4), (13) and (15).

The dyes or dye mixtures of the invention are useful for dyeing and printing manufactured natural polymer and especially synthetic hydrophobic fibre materials, especially

textile materials. Textile materials composed of blend fabrics comprising such manufactured natural polymer or synthetic hydrophobic textile materials are likewise dyeable or printable with the dyes or dye mixtures of the invention.

Useful manufactured natural polymer textile materials are especially cellulose acetate and cellulose triacetate.

Synthetic hydrophobic textile materials are especially linear aromatic polyesters, for example polyesters formed from a terephthalic acid and glycols, particularly ethylene glycol, or condensation products of terephthalic acid and

1,4-bis(hydroxymethyl)cyclohexane; polycarbonates, for example those formed from α,α -dimethyl-4,4-dihydroxydiphenylmethane and phosgene; or fibres based on polyvinyl chloride or polyamide.

The dyes or dye mixtures of the invention are applied to the textile materials according to known dyeing processes. For example, polyester fibres are exhaust dyed from an aqueous dispersion in the presence of customary anionic or nonionic dispersants with or without customary carriers at temperatures between 80 and 140°C. Cellulose acetate is preferably dyed at between about 65 to 85°C and cellulose triacetate at up to 115°C.

The dyes or dye mixtures of the invention dye adjacent wool and cotton only minimally, if at all, i.e., exhibit a very good wool and cotton reserve, so that they may also be used to good effect for dyeing polyester-wool and polyester-cellulosic blend fabrics.

The dyes or dye mixtures of the invention are useful for dyeing by the thermosol, exhaust and continuous processes and for printing processes. The exhaust process is preferred. The liquor ratio depends on the apparatus, the substrate and the make-up form. However, the liquor ratio can be chosen to be within a wide range, for example in the range from 4:1 to 100:1, but it preferably is between 6:1 to 25:1.

The textile material mentioned may be present in the various processing forms, for example as a fibre, yarn or web or as a woven or loop-formingly knitted fabric.

It is advantageous to convert the dyes or dye mixtures of the invention into a dye preparation before use. For this, the dyes are ground so that their particle size is on average between 0.1 and 10 microns. The grinding may be effected in the presence of dispersants. For example, the dried dye is ground with a dispersant or kneaded in paste form with a dispersant and then dried under reduced pressure or by spray drying. The preparations thus obtained can be used to prepare print pastes and dye-baths by adding water.

Printing utilizes the customary thickeners, for example modified or nonmodified natural products, for example alginates, British gum, gum arabic, crystal gum, carob bean flour, tragacanth, carboxymethylcellulose, hydroxyethylcellulose, starch or synthetic products, for example polyacrylamides, polyacrylic acid or copolymers thereof or polyvinyl alcohols.

The dyes or dye mixtures of the invention confer on the materials mentioned, especially on polyester material, level shades having very good service fastnesses, such as in particular good light fastness, especially a very good hot light fastness, fastness to dry heat setting and pleating, chlorine fastness and wet fastness such as fastness to water, perspiration and washing; the dyeings are further characterized by good rub fastness and heat stability.

The dyes or dye mixtures of the invention are also very useful for preparing combination shades together with other dyes. More particularly, the dyes of the invention can be used as a suitable component in a trichromatic dyeing or printing technique.

The aforementioned use of the dyes or dye mixtures according to the invention forms as much a part of the subject-matter of the present invention as a process for dyeing or printing manufactured natural polymer or synthetic hydrophobic fibre material,

especially textile material, which comprises applying the dyes or dye mixtures of the invention to the material mentioned or to incorporate them into it. The hydrophobic fibre material mentioned is preferably textile polyester material. Further substrates useful for treatment by the process of the invention and also preferred process conditions are to be found above under the more particular description of the use of the dyes or dye mixtures according to the invention.

The present invention further provides a process for preparing coloured plastics or polymeric colour particles, which is characterized in that it comprises blending a high molecular weight organic material and a colouristically effective amount of at least one anthraquinone dye of the formula (1) with each other.

The high molecular weight organic substances are coloured with the anthraquinone dye of the formula (1) by, for example, mixing such an anthraquinone dye into these substrates using roll mills or mixing or grinding apparatus whereby the anthraquinone dye is dissolved or finely dispersed in the high molecular weight material. The high molecular weight organic material with the admixed anthraquinone dye is then processed in a conventional manner, for example by calendering, pressing, extrusion, spread coating, spinning, casting or injection moulding, whereby the coloured material acquires its ultimate shape. The admixing of the anthraquinone dye can also be effected directly prior to the actual processing step, for example by continuously metering a pulverulent anthraquinone dye and a granulated or pulverulent high molecular weight organic material and also optionally additional substances such as for example additives simultaneously directly into the inlet zone of an extruder where the mixing-in takes place just prior to the processing. In general, however, prior mixing of the anthraquinone dye into the high molecular weight organic material is preferable, since more uniformly coloured substrates are obtainable.

It is frequently desired to incorporate plasticizers into the high molecular weight compounds prior to shaping to produce non-rigid mouldings or to reduce their brittleness. Examples of useful plasticizers are esters of phosphoric acid, phthalic acid or sebacic acid. In the process of the invention, plasticizers can be incorporated into the po-

lymers before or after the colorant has been incorporated. It is further possible, for the purpose of achieving different hues, to add to the high molecular weight organic substances not only the anthraquinone dye of the formula (1) but also further anthraquinone dyes or other colorants in any desired quantities, optionally together with further additives such as for example fillers or siccatives.

It is preferable to colour thermoplastic materials in the form of fibres especially. Preferred high molecular weight organic materials useful for coloration according to the invention are very generally polymers having a dielectric constant ≥ 2.5 , especially polyester, polycarbonate (PC), polystyrene (PS), polymethyl methacrylate (PMMA), polyamide, polyethylene, polypropylene, styrene/acrylonitrile (SAN) or acrylonitrile/butadiene/styrene (ABS). Particular preference is given to polyester and polyamide. Very particular preference is given to linear aromatic polyesters obtainable by polycondensation of terephthalic acid and glycols, especially ethylene glycol, or condensation products of terephthalic acid and 1,4-bis-(hydroxymethyl)cyclohexane, for example polyethylene terephthalate (PET) or polybutylene terephthalate (PBTP); polycarbonates, for example polycarbonates formed from α,α -dimethyl-4,4-dihydroxydiphenylmethane and phosgene; or polymers based on polyvinyl chloride or polyamide, for example nylon 6 or nylon 66.

The invention further provides the dyed or printed hydrophobic fibre material, preferably polyester textile material, and also the mass-coloured plastics provided by the aforementioned processes.


The dyes or dye mixtures of the invention are also useful for modern recording processes, for example thermal transfer printing.

The examples hereinbelow illustrate the invention. Parts and percentages are by weight, unless otherwise stated. Temperatures are in degrees Celsius. Parts by weight relate to parts by volume as the gram relates to the cubic centimetre.

Preparation Example 1:

13.3 parts by weight of 1-amino-4-thiophenylantraquinone are suspended in 70 parts by weight of nitrobenzene. The resultant violet suspension is admixed with 8.2 parts by weight of 2-chlorobenzoyl chloride and heated to 150°C. Substantial evolution of gas commences at 90°C. The reaction mixture is maintained at 150°C for 30 minutes and then cooled down to 70°C. At 70°C, 70 parts by weight of methanol are carefully added dropwise and the mixture is cooled down to 40°C. The suspension is then filtered off and washed with methanol and dried.

This provides 16.7 parts by weight of compound of formula




(4),

which dyes polyester in lightfast red shades.

Preparation Example 2:

Example 1 is repeated except that the 8.2 parts by weight of 2-chlorobenzoyl chloride are replaced by 8.2 parts by weight of 3-chlorobenzoyl chloride. This provides 16.7 parts by weight of the compound of the formula



(13),

which likewise dyes polyester in lightfast red shades.

Coloration Example 1:

1 g of the anthraquinone dye described in Preparation Example 1 is sand milled together with 17 g of water and 2 g of a commercially available dinaphthylmethanesulfonate dispersant and converted into a 5% aqueous dispersion.

This formulation is used to prepare a 1% dyeing on polyester at 130°C in a high temperature exhaust process, followed by reduction clearing.

The red dyeing thus obtained comprises very good service fastnesses and especially an excellent light fastness.

Coloration Example 2:

1200.00 g of polyester chips (PET Amite D04-300, DSM) are predried at 130°C for 4 hours and subsequently mixed with

0.24 g of the pigment dye of the formula (4)

in a roller rack at 60 revolutions per minute for 15 minutes until homogeneous.

The homogeneous mixture is extruded on a twin screw 25 mm extruder (from Collin, D-85560 Ebersberg) comprising 6 heating zones at a maximum temperature of 275°C, quenched with water, granulated in a Turb Etuve TE 25 granulator (from MAPAG AG, CH-3001 Bern) and subsequently dried at 130°C for 4 hours.

This provides red polyester chips having good allround fastnesses, especially very good light and hot light fastnesses.

Coloration Example 3:

1200.00 g of polyester chips (PET Amite D04-300, DSM) are predried at 130°C for 4 hours and subsequently mixed with

0.24 g of a dye mixture containing

0.08 g of the pigment dye of the formula (4),

0.08 g of the pigment dye of the formula (13) and

0.08 g of the pigment dye of the formula (15),

in a roller rack at 60 revolutions per minute for 15 minutes until homogeneous.

The homogeneous mixture is extruded on a twin screw 25 mm extruder from (Collin, D-85560 Ebersberg) comprising 6 heating zones at a maximum temperature of


- 14 -

275°C, quenched with water, granulated in a Turb Etuve TE 25 granulator (from MAPAG AG, CH-3001 Bern) and subsequently dried at 130°C for 4 hours.

This provides red polyester chips having good allround fastnesses, especially very good light and hot light fastnesses.

What is claimed is:


1. Anthraquinone dyes of the formula



where

R_1 is hydrogen, R_2 is hydrogen or $-\text{CO}-\text{C}_2-\text{C}_6\text{alkyl}$ wherein the $\text{C}_2-\text{C}_6\text{alkyl}$ moiety may


be substituted by carboxyl, or is




wherein R_6 is hydrogen,

$\text{C}_1-\text{C}_4\text{alkyl}$, hydroxyl, carboxyl or halogen, R_7 is hydrogen, $\text{C}_1-\text{C}_4\text{alkyl}$ or halogen and R_8 is hydrogen or $\text{C}_2-\text{C}_3\text{alkyl}$ or when R_4 is halogen R_8 may be methyl or halogen, R_3 is hydrogen or halogen, R_4 is hydrogen or halogen and n is 0, 1 or 2, with the proviso that R_3 , R_4 , R_6 , R_7 and R_8 are not all hydrogen at one and the same time.


2. Anthraquinone dyes according to claim 1 of the formulae




- 16 -




(3),



(4),




(5),




(6),


- 17 -




(7),



(8),




(9),




(10),


- 18 -




(11),



(12),




(13) and



(14).

3. A process for preparing the dyes of the formula (1) according to claim 1, characterized in that it comprises reacting a compound of the formula



where

R_3 , R_4 and n are each as defined under the formula (1), with the compound of the formula



where

R_6 , R_7 and R_8 are each as defined under the formula (1).

4. A dye mixture comprising two or more structurally different anthraquinone dyes of formula (1) according to claim 1.
5. The use of the dyes of the formula (1) according to claim 1 or of a dye mixture according to claim 4 for dyeing or printing manufactured natural polymer or synthetic hydrophobic fibre materials.
6. Manufactured natural polymer or synthetic hydrophobic fibre materials dyed or printed with the dyes of the formula (1) according to claim 1 or with a dye mixture according to claim 4.
7. A process for preparing coloured plastics or polymeric colour particles, characterized in that it comprises incorporating one or more anthraquinone dyes of the formula (1) into these materials.

- 20 -

8. The use of the anthraquinone dyes of formula (1) according to claim 1 or of a dye mixture according to claim 4 for preparing coloured plastics or polymeric colour particles.

9. Plastics or polymeric colour particles coloured as per claim 8 with an anthraquinone dye of the formula (1) according to claim 1 or with a dye mixture according to claim 4.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 01/14692

A. CLASSIFICATION OF SUBJECT MATTER
 IPC 7 C09B1/58 C08K5/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C09B C08K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

CHEM ABS Data, EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

| Category * | Citation of document, with indication, where appropriate, of the relevant passages | Relevant to claim No. |
|------------|--|-----------------------|
| X | FR 2 369 314 A (CIBA GEIGY AG) 26 May 1978 (1978-05-26) page 3, line 15 -page 7, line 33; claims 1-4,9; examples 89-91,98 | 1-9 |
| X | DE 33 14 467 A (BAYER AG) 19 January 1984 (1984-01-19) Table 3, page 62, compounds 16,18,26 | 1,4-9 |
| X | CH 369 741 A (BASF AG) 28 February 1963 (1963-02-28) page 2, line 29 - line 31; examples 1-3 | 1,4-6 |

☐ Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"Z" document member of the same patent family

Date of the actual completion of the international search

25 April 2002

Date of mailing of the international search report

07/05/2002

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
 Fax: (+31-70) 340-3016

Authorized officer

Ginoux, C

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 01/14692

| Patent document cited in search report | | Publication date | Patent family member(s) | Publication date |
|---|---|---------------------|----------------------------|---------------------|
| FR 2369314 | A | 26-05-1978 | CH 624436 A5 | 31-07-1981 |
| | | | CA 1111166 A1 | 20-10-1981 |
| | | | DE 2748834 A1 | 03-05-1978 |
| | | | FR 2369314 A1 | 26-05-1978 |
| | | | GB 1558354 A | 28-12-1979 |
| | | | IT 1088962 B | 10-06-1985 |
| | | | JP 53057254 A | 24-05-1978 |
| | | | US 4176113 A | 27-11-1979 |
| DE 3314467 | A | 19-01-1984 | DE 3314467 A1 | 19-01-1984 |
| | | | DE 3381845 D1 | 04-10-1990 |
| | | | EP 0103095 A2 | 21-03-1984 |
| | | | JP 59027956 A | 14-02-1984 |
| CH 369741 | A | 28-02-1963 | DE 1223797 B | 01-09-1966 |
| | | | BE 595479 A | |
| | | | FR 1268400 A | 28-07-1961 |
| | | | GB 905449 A | 12-09-1962 |